

# LEATHER THICKNESS CONVERSION

EXCEPTIONAL LEATHER SINCE 1927

1 oz. Thickness Equivalents			
0.40 mm	75.00 iron	1/64"	0.02"
2 oz. Thickness Equivalents			
0.80 mm	1.50 iron	1/32"	0.03"
3 oz. Thickness Equivalents			
1.20 mm	2.25 iron	3/64"	0.05"
4 oz. Thickness Equivalents			
1.60 mm	3.00 iron	1/16"	0.06"
5 oz. Thickness Equivalents			
2.00 mm	3.75 iron	5/64"	0.08"
6 oz. Thickness Equivalents			
2.40 mm	4.50 iron	3/32"	0.09"
7 oz. Thickness Equivalents			
2.80 mm	5.25 iron	7/64"	0.11"
8 oz. Thickness Equivalents			
3.20 mm	6.00 iron	1/8"	0.13"
9 oz. Thickness Equivalents			
3.60 mm	6.75 iron	9/64"	0.14"

10 oz. Thickness Equivalents			
4.00 mm	7.50 iron	5/32"	0.16"
11 oz. Thickness Equivalents			
4.40 mm	8.25 iron	11/64"	0.17"
12 oz. Thickness Equivalents			
4.80 mm	9.00 iron	3/16"	0.19"
13 oz. Thickness Equivalents			
5.20 mm	9.75 iron	13/64"	0.20"
14 oz. Thickness Equivalents			
5.60 mm	10.50 iron	7/32"	0.22"
15 oz. Thickness Equivalents			
6.00 mm	11.25 iron	15/64"	0.23"
16 oz. Thickness Equivalents			
6.40 mm	12.00 iron	1/4"	0.25"
17 oz. Thickness Equivalents			
6.80 mm	12.75 iron	17/64"	0.27"



MILTON SOKOL

SINCE 1927